

01.01.2022



Transfer Special

Removable (RR23)

Characteristics Label

Label material Transfer Special removable (RR23)

Raw material 1912027 Adhesive bond Rolls

Product White woodfree machine coated mid-gloss paper.

Use Designed for quality multicolour labels requiring high contrast and fine printing

detail.

Typical technical values

80	g/m²	ISO 536	
70	μm	ISO 534	
5.8	kN/m	ISO 1924/1	
2.8	kN/m	ISO 1924/1	
90	%	ISO 2470/1	
1.0	μm	ISO 8791	PPS 10
88	%	ISO 2471	
64	%	Hunter75°	
120	%	ISO 11475	
0.23	nMn	ISO/DP 2493	
0.13	nMn	ISO/DP 2493	
	70 5.8 2.8 90 1.0 88 64 120 0.23	70 μm 5.8 kN/m 2.8 kN/m 90 % 1.0 μm 88 % 64 % 120 % 0.23 nMn	70 μm ISO 534 5.8 kN/m ISO 1924/1 2.8 kN/m ISO 1924/1 90 % ISO 2470/1 1.0 μm ISO 8791 88 % ISO 2471 64 % Hunter75° 120 % ISO 11475 0.23 nMn ISO/DP 2493

Printability Suitable for flexography, offset, rotogravure, screen and hot foil. Suitable for

thermal transfer printing with wax/resin ribbons. Testing recommended.

Characteristics Adhesive

Adhesive Removable

Type Removable adhesive. Composition Acrylic, water borne.

Use Designed for labelling wide variety of substrates where good long term

removability is required. Good adhesion to fiber based substrates and curved

surfaces.



Typical technical values

Tack	5	N/25mm FTM 9	
Peel min.	2.0	N/25mm FTM 2	90°
Peel max.	5.0	N/25mm FTM 2	90°
Labeling temp. min.	5	°C	
Service temp. min.	-10	°C	
Service temp. max.	80	°C	

Limitations Due to diversity of fiber based substrates such as cardboard, it is recommended to

perform an application test before using.

Approvals For food packaging applications, please contact your local sales representative for

the individual Declaration of Conformance (DoC) document for further compliance

information.

Characteristics Glassine

Backing HONEY GLASSINE 65

Product Yellow transparent glassine backing paper.

Use Designed for all reelstock applications; suitable for automatic dispensing.

Typical technical values

Substance	57	g/m²	ISO 536
Caliper	51	μm	ISO 534
Tensile strength MD	6.2	kN/m	ISO 1924
Tensile strength CD	2.3	kN/m	ISO 1924
Transparency	49	%	DIN 53147

Shelf life From date of manufacture: 12 months, under FINAT defined storage conditions

(+20-25° C and RH 40-50 %). Prolonged storage at higher temperatures and/or

humidity levels will shorten the shelf life.



Disclaimer

The performance of the product should always be tested in the actual application conditions. Our recommendations are based on our most current knowledge and experience. As our products are used in conditions beyond our control, we cannot assume any liability for damage caused through their use. Users of our products are solely responsible that the product is suitable for its intended application, and have determined such at their sole discretion. Users must comply with any applicable legislation and/or testing requirements for the finished article, and are responsible for bringing their products to market.

This publication does not constitute any warranty, express or implied, and is intended only for the recipient and cannot therefore be transferred to any third party. We cannot assume any liability for the use of our products in conjunction with other materials.

All our products are sold subject to Carl Valentin's general sales conditions, and you should ensure that any existing laws are observed.

This publication replaces all previous versions. All information is subject to change without notice.



Carl Valentin GmbH

Neckarstraße 78 – 86 u. 94

78056 Villingen-Schwenningen

Phone + 49 7720 9712 - 0 . Fax + 49 7720 9712 – 9901

info@carl-valentin.de www.carl-valentin.de

